

RADIO TRANSPARENCY

No.	Product name	Glass Build-Up Outer/Cavity/Mid/Cavity/Inner	EN 673	EN 410					EN ISO 717-1	Thickness mm	Weight kg/m ²
			U _g -Value	Light transmission	g-Value	Light Reflection external	Light Reflection internal	Colour Rendering Index _{Ra}	Sound Insulation R _w / C / C _r		
			W/(m ² K)	%	%	%	%		dB		
100	arconnect N34 // 1,2 ⁷⁾	4 / 16 / :4	1,2	82	65	12	12	98	32	24	20
101	arconnect N10 // 1,2 ⁷⁾	4 / 16 / :4	1,2	70	51	22	23	97	32	24	20
108	arconnect N34 /// 0,7 ⁷⁾	4: / 14 / 4 / 14 / :4	0,7	74	54	15	15	97	32 / -1 / -4	40	30
109	arconnect N10 /// 0,7 ⁷⁾	4: / 14 / 4 / 14 / :4	0,7	56	37	32	32	95	32 / -1 / -4	40	30

7) See also the flyer: arconnect® (www.arcon-glas.de/en).